

## V.N.12 Hydrogen Purification Using Advanced Polymeric Membranes

Benny D. Freeman (Primary Contact),  
Haiqing Lin, Victor A. Kusuma,  
Scott T. Matteucci, Roy D. Raharjo,  
Scott D. Kelman

Center for Energy and Environmental Resources,  
University of Texas at Austin  
10100 Burnet Road  
Austin, TX 78758  
Phone: (512) 232-2803; Fax: (512) 232-2807  
E-mail: freeman@che.utexas.edu

DOE Program Officer: William Millman

Phone: (301) 903-5805  
E-mail: william.millman@science.doe.gov

### Objectives

Acid gases like CO<sub>2</sub> are major impurities in gas streams containing hydrogen, and membrane-based separation may be utilized to remove these acid gases. One strategy for acid gas removal from mixtures with light gases takes advantage of the affinity of acid gases for polar groups, such as ether oxygens incorporated within polymeric membranes. Our research on cross-linked poly(ethylene oxide) revealed good separation performance in removing CO<sub>2</sub> from CO<sub>2</sub>/H<sub>2</sub> mixtures and indicated possible further performance improvement by engineering the molecular structure of such materials. To achieve this goal, we are pursuing a fundamental study of the effect of various structure modification strategies on the transport properties of cross-linked poly(ethylene oxide). In addition, we are exploring other materials with novel separation properties that may contribute to our understanding in this field, such as membranes containing nanoparticles.

### Technical Barriers

Our initial research has shown the viability of cross-linked poly(ethylene oxide) for CO<sub>2</sub> removal from H<sub>2</sub> and suggests that fundamental understanding of the relationship between network structure, polymer chemical composition and transport properties may yield even better materials.

### Abstract

Rubbery cross-linked poly(ethylene oxide) facilitates separation of CO<sub>2</sub> from mixtures with light gases and exhibits favorable CO<sub>2</sub>/H<sub>2</sub> separation properties. Because the separation is largely due to an affinity

between CO<sub>2</sub> and polar groups in the membrane, unlike conventional polymers, plasticization of the material by CO<sub>2</sub> improves separation properties, especially at lower temperatures and high partial pressures of CO<sub>2</sub>. In addition, we have explored the separation of other polar and condensable gases from mixtures with lighter gases.

### Progress Report

Our progress in cross-linked poly(ethylene oxide) (XLPEO) for CO<sub>2</sub>/H<sub>2</sub> separation is summarized in a recent paper [1]. Harnessing CO<sub>2</sub>'s affinity for polar groups within the polymer membrane underlies CO<sub>2</sub> removal using rubbery XLPEO [2], which has higher gas permeability than conventional membranes and exhibits weak size-sieving ability [3]. In these materials, CO<sub>2</sub> is preferentially permeated over H<sub>2</sub>. Additionally, plasticization actually improves CO<sub>2</sub>/H<sub>2</sub> separation by further reducing size-sieving ability and increasing permeability [1].

XLPEO is formed by photopolymerization of poly(ethylene glycol) diacrylate (PEGDA) [4]. Cross-linking eliminates crystallization of EO units that otherwise occurs in high molecular weight poly(ethylene oxide) (PEO), leading to reduced permeability [3] and reduced CO<sub>2</sub>/H<sub>2</sub> selectivity [1, 2, 5]. In addition, PEGDA can be copolymerized with mono-functionalized PEO-bearing acrylates, such as poly(ethylene glycol) acrylate (PEGA) [4] or poly(ethylene glycol) methyl ether acrylate (PEGMEA) [1, 4]. While gas solubility in the membrane does not change with copolymer composition [6], diffusivity through the membrane changes strongly with polymer composition [7]. For instance, increasing PEGMEA content in PEGDA copolymer increases the fractional free volume (FFV) [8, 9] and, in turn, the CO<sub>2</sub> permeability and CO<sub>2</sub>/H<sub>2</sub> selectivity.

Plasticization effects are demonstrated through pure and mixed-gas studies of the PEGDA/PEGMEA copolymers, where CO<sub>2</sub> and H<sub>2</sub> permeability increases are observed with increasing CO<sub>2</sub> partial pressure [1]. This effect is more significant at lower temperatures due to increased CO<sub>2</sub> condensability, leading to higher CO<sub>2</sub> sorption in the polymer [1, 6]. At low temperature and high CO<sub>2</sub> partial pressure, the increase in CO<sub>2</sub>/H<sub>2</sub> selectivity is accompanied by high CO<sub>2</sub> permeability [1], which takes the performance above the separation 'upper bound' [1]. Additional mixed-gas studies explored the removal of CO<sub>2</sub> from other gases (such as CH<sub>4</sub> [10] and C<sub>2</sub>H<sub>6</sub> [11]) using XLPEO, with similarly favorable performance. Plasticization effects are also observed when other polar impurities, such as H<sub>2</sub>O and H<sub>2</sub>S, are introduced [1].

Similar separation behavior was observed in cross-linked poly(propylene oxide) (XLPPPO) made from acrylate analogues of poly(propylene glycol) [12]. However, although XLPPPO in general displays slightly higher CO<sub>2</sub> permeability than pure cross-linked PEGDA, it has lower CO<sub>2</sub>/H<sub>2</sub> selectivity than the XLPEO series, despite having higher FFV [12].

Our work on the gas transport behavior of nanocomposites is based on polymers such as 1,2-polybutadiene (PB). Neutral TiO<sub>2</sub> nanoparticles and basic MgO nanoparticles have been used to increase light gas solubility and permeability in heterogeneous membranes [13-16]. For instance, PB containing 27 vol.% TiO<sub>2</sub> has CO<sub>2</sub> permeability roughly 3 times higher than that of the unfilled polymer, while its CO<sub>2</sub>/H<sub>2</sub> selectivity remains approximately equivalent to the unfilled polymer [14]; similar behavior was observed when MgO nanoparticles were added to PB [15]. Both the permeability and selectivity behavior in nanocomposite PB are due partly to higher light gas solubility in the nanocomposites than in unfilled PB.

Poly(1-trimethylsilyl-1-propyne) (PTMSP) is exceptional among glassy polymers for its very high free volume and gas permeability. Although its outstanding vapor/gas selectivity favors the transport of higher hydrocarbons from mixtures with H<sub>2</sub> and CH<sub>4</sub> [17], PTMSP is easily dissolved by many organic solvents. To improve its chemical stability, PTMSP can be cross-linked using bis-azides, but this method reduces gas diffusivity and permeability [17]. Adding nanoparticles such as TiO<sub>2</sub> and fumed silica to PTMSP increases its gas permeability due to an increase in diffusivity [13].

## Future Work

Our future studies on XLPEO will focus on the effects of further structural modifications on transport properties. Specifically, the monomer EO length can be varied to modify XLPEO's cross-link density (which affects chain dynamics [8]), polar content, or crystallinity. Given the significant difference in transport properties between PEGDA copolymerized with PEGA and with PEGMEA [7], another way to modify XLPEO structure is to change the terminal end-group of the monoacrylate copolymer.

We are also exploring incorporation of nanoparticles into XLPEO to further improve separation performance. As polymer-particle interaction is a significant determinant of the resulting membrane properties, it is important to understand this phenomenon to control the resulting properties.

## References and Publications

1. H. Lin, E. Van Wagner, B. D. Freeman, L. G. Toy, R. P. Gupta, Plasticization-Enhanced H<sub>2</sub> Purification Using Polymeric Membranes, *Science* **2006**, *311*, 639-642.
2. H. Lin, B. D. Freeman, Materials Selection Guidelines for Membranes that Remove CO<sub>2</sub> from Gas Mixtures, *Journal of Molecular Structure* **2005**, *739*, 57-74.
3. H. Lin, B. D. Freeman, Gas Solubility, Diffusivity and Permeability in Poly(ethylene oxide), *Journal of Membrane Science* **2004**, *239*, 105-117.
4. H. Lin, E. Van Wagner, J. S. Swinnea, B. D. Freeman, S. J. Pas, A. J. Hill, S. Kalakkunnath, D. S. Kalika, Transport and Structural Characteristics of Crosslinked Poly(ethylene oxide) Rubbers, *Journal of Membrane Science* **2006**, *276*, 145-161.
5. S. Kalakkunnath, D. S. Kalika, H. Lin, B. D. Freeman, Viscoelastic Characteristics of U.V. Polymerized Poly(ethylene glycol diacrylate) Networks with Varying Extents of Crosslinking, *Journal of Polymer Science: Part B: Polymer Physics* **2006**, *44*, 2058-2070.
6. H. Lin, B. D. Freeman, Gas and Vapor Solubility in Crosslinked Poly(ethylene glycol Diacrylate), *Macromolecules* **2005**, *38*, 8394-8407.
7. H. Lin, B. D. Freeman, Gas Permeation and Diffusion in Crosslinked Poly(ethylene glycol Diacrylate), *Macromolecules* **2006**, *39*, 3568-3580.
8. S. Kalakkunnath, D. S. Kalika, H. Lin, B. D. Freeman, Segmental Relaxation Characteristics of Crosslinked Poly(ethylene oxide) Copolymer Networks, *Macromolecules* **2005**, *38*, 9679-9687.
9. V. A. Kusuma, H. Lin, B. D. Freeman, M. Jose-Yacaman, S. Kalakkunnath, D. S. Kalika, in *Membranes: Manufacturing Utilizing Six Sigma and Applications* (Eds.: N. Li, A. G. Fane, W. S. W. Ho, T. Matsuura), Wiley, in press.
10. H. Lin, E. Van Wagner, R. Raharjo, B. D. Freeman, I. Roman, High Performance Polymer Membranes for Natural Gas Sweetening, *Advanced Materials* **2006**, *18*, 39-44.
11. S. D. Kelman, H. Lin, E. D. Sanders, B. D. Freeman, CO<sub>2</sub>/C<sub>2</sub>H<sub>6</sub> Separation Using Solubility Selective Membranes, in preparation.
12. R. D. Raharjo, H. Lin, D. F. Sanders, B. D. Freeman, S. Kalakkunnath, D. S. Kalika, Relation Between Network Structure and Gas Transport in Crosslinked Poly(propylene glycol Diacrylate), *Journal of Membrane Science* **2006**, *283*, 253-265.
13. S. Matteucci, V. A. Kusuma, D. Sanders, B. D. Freeman, Gas Transport Properties of TiO<sub>2</sub> Nanoparticle Filled Poly(1-trimethylsilyl-1-propyne), *Journal of Membrane Science* **2007**, submitted.

14. S. Matteucci, V. A. Kusuma, B. D. Freeman, Permeability Enhancements in 1,2-Polybutadiene Containing Brookite Nanoparticles, in preparation.
15. S. Matteucci, R. Raharjo, V. A. Kusuma, S. Swinnea, B. D. Freeman, A. J. Hill, Magnesium Oxide Nanoparticle Induced Permeability Enhancements in 1,2 Polybutadiene, in preparation.
16. S. Matteucci, V. Kusuma, B. D. Freeman, A. J. Hill, S. Kalakkunnath, D. S. Kalika, Gas Separation Properties of Polymer Nanocomposites, *PMSE Preprints* **2006**, *94*, 621.
17. S. D. Kelman, B. D. Freeman, Crosslinking Poly(1-trimethylsilyl-1-propyne) and its Effect on Chemical Stability and Transport Properties, in preparation.

#### Additional Publications Not Included as References

18. S. Kalakkunnath, D. S. Kalika, H. Lin, R. D. Raharjo, B. D. Freeman, Molecular Relaxation in Cross-linked Poly(ethylene glycol) and Poly(propylene glycol) Diacrylate Networks by Dielectric Spectroscopy, *Polymer* **2007**, *48*, 579-589.
19. R. D. Raharjo, B. D. Freeman, E. S. Sanders, "Pure and Mixed Gas CH<sub>4</sub> and n-C<sub>4</sub>H<sub>10</sub> Sorption and Dilation in Poly(dimethylsiloxane)", *Journal of Membrane Science* **2007**, in press.
20. X.-Y. Wang, F. T. Willmore, R. D. Raharjo, X. Wang, B. D. Freeman, A. J. Hill, and I. Sanchez, "Molecular Simulation of Physical Aging in Polymer Membrane Materials," *J. Phys. Chem. B* **2006**, *110*, 16685-16693.
21. X.-Y. Wang, R. D. Raharjo, H. J. Lee, Y. Lu, B. D. Freeman, and I. C. Sanchez, "Molecular Simulation and Experimental Study of Substituted Polyacetylenes: Fractional Free Volume, Cavity Size Distribution and Diffusion Coefficients," *J. Phys. Chem. B* **2006**, *110*, 12666-12672.
22. J. C. Jansen, M. Macchione, R. Raharjo, B. D. Freeman, and E. Drioli, "Pure and Mixed Gas Transport Properties of Novel Asymmetric Poly(ether ether ketone) Membranes with Different Morphologies", *Desalination* **2006**, *199(1-3)*, 461-463.
23. R. D. Raharjo, H. J. Lee, B. D. Freeman, T. Sakaguchi, T. Masuda, "Pure Gas and Vapor Permeation Properties of Poly[1-phenyl-2-[p-(trimethylsilyl)phenyl]acetylene] (PTMSDPA) and Its Desilylated Analog, Poly[diphenylacetylene] (PDPA)", *Polymer* **2005**, *46*, 6316-6324.
24. R. S. Prabhakar, R. Raharjo, L. G. Toy, H. Lin, B. D. Freeman, "Self-Consistent Model of Concentration and Temperature Dependence of Permeability in Rubbery Polymers", *Industrial & Engineering Chemistry Research* **2005**, *44*, 1547-1558.
25. R. D. Raharjo, B. D. Freeman, E. S. Sanders, "Mixed Gas n-C<sub>4</sub>H<sub>10</sub>/CH<sub>4</sub> Permeation and Diffusion in Poly(dimethylsiloxane)", in preparation.
26. S. Matteucci, Yu. Yampolskii, B. D. Freeman, and I. Pinnau, "Transport of Gases and Vapors in Glassy and Rubbery Polymers" in *Materials Science of Membranes for Gas and Vapor Separation* (Eds.: B. D. Freeman, I. Pinnau, Yu. Yampolskii), John Wiley & Sons **2006**, pp. 1-49.
27. H. Lin, S. Matteucci, B. D. Freeman, S. Kalakkunnath, D. S. Kalika, "Novel Membrane Materials for CO<sub>2</sub> Removal from Mixtures with H<sub>2</sub>", *Preprints of Symposia - American Chemical Society, Division of Fuel Chemistry* **2005**, *50(2)*, 617-619.
28. S. Matteucci, E. Van Wagner, B. D. Freeman, T. Sakaguchi, and T. Masuda, "Desilylation of Substituted Polyacetylenes in the Presence of Nanoparticles", *Macromolecules*, in press.
29. S. Matteucci, M. Andrews, B. D. Freeman, and J. Lin, "Materials Science of Organic and Inorganic Membranes for CO<sub>2</sub> Separations", *Journal of Membrane Science*, in preparation.