

II.K.12 Hydrogen Generation Using Integrated Photovoltaic and Photoelectrochemical Cells

Jin Z. Zhang^{1*} (Principal Investigator) and Yiping Zhao²

¹Department of Chemistry and Biochemistry
University of California
1156 High Street
Santa Cruz, CA 95064
Phone: (831) 459-3776
E-mail: zhang@ucsc.edu

²Department of Physics and Astronomy
The University of Georgia
Athens, GA 30602
Phone: (706) 542-7792
E-mail: zhaoy@physast.uga.edu

DOE Program Manager: Jane Zhu
Phone: (301) 903-3811
E-mail: Jane.Zhu@science.doe.gov

tentatively attributed to increased light scattering of Au NPs, leading to enhanced light absorptions of the CdSe QDs.²

Abstract

Hydrogen is an extremely attractive fuel for clean alternative energy. New nanocomposite structures and advanced strategies have been developed to improve the performance of PEC cells for hydrogen generation from water splitting. Systematical studies have been carried out to probe the fundamentals behind, including charge carrier properties at interfaces. One of the most important discoveries we have made is strong synergistic effects in ternary nanocomposites that show significantly enhanced PEC properties compared to binary or single component systems. These strategies are promising for advancing energy conversion technologies in the future.

Objectives

The primary objective of this project is to develop novel nanostructures with improved optical and electronic properties for photoelectrochemical (PEC) hydrogen generation from water splitting. Specifically, we seek to design and demonstrate new strategies based on combining quantum dot (QD)-sensitization and elemental doping to significantly enhance visible light absorption and thereby PEC properties of metal oxide (MO) nanostructures, e.g. TiO₂, WO₃, and ZnO. Interesting synergistic effect has been discovered from the combined use of QD sensitization and N-doping of TiO₂ nanoparticle (NP) and nanorods.¹ Similarly, combining Au NPs with CdSe QD sensitization of TiO₂ has shown strong synergistic effect as well in terms of PEC performance.² The fundamental mechanisms behind the observed synergistic effects have been proved using a combination of experimental techniques including spectroscopy, microscopy, and ultrafast laser.

Technical Barriers

Towards the development of efficient PEC cells for hydrogen generation based on nanomaterials, one of the technical barriers is to control the surface properties of all the components involved, e.g. the MO nanostructures, QDs, and metal NPs. The second technical barrier is to determine the local structures and exact energy levels of the dopant, e.g. N, since this is critical to develop appropriate models to explain the synergistic effects observed.¹ The third technical barrier is to probe and understand the exact role of metal NPs in the enhanced PEC performance, which has been

Progress Report

1. Generating hydrogen by PEC with CdSe QD sensitized and N-doped TiO₂ nanostructures

TiO₂ is the most researched material for PEC water splitting. Since the bandgap of the TiO₂ is large ($E_g=3.2\text{eV}$), it cannot absorb most of the sunlight. One effective way to increase the absorption of the sunlight is by using semiconductor QDs to sensitize the TiO₂ film. Another approach is elemental doping. PEC measurements carried out on TiO₂ NPs and nanorods demonstrated that there is a strong synergistic effect when QD sensitization is combined with N-doping.¹ The reason for the increase in photocurrent when CdSe sensitizes N-doped TiO₂ vs. TiO₂ alone is attributed to the increase in hole transport from the valence band of CdSe to the oxygen vacancies in N-doped TiO₂.

2. PEC Properties of CdSe/TiO₂ Mesoporous Hybrid Structures

In sensitizing metal oxides such as TiO₂ using QDs, small molecules are often used to link semiconductor quantum dots to TiO₂ films. Since these small molecules are mainly dielectric materials, they will block the transfer of the photoelectrons from the quantum dots to the TiO₂ film. In this project, we have developed a new method to link QDs and TiO₂ without using the small linking molecules by assembly the QDs and TiO₂ NPs together into colloid spheres.² The PEC characterization of CdSe/TiO₂ hybrid spheres shows an increase in the photocurrent when compared to TiO₂ alone and CdSe sensitized to TiO₂ using a linking molecule. The overall increase in photocurrent

from the CdSe/TiO₂ hybrid structure is believed to be due to better or stronger coupling between the CdSe and the TiO₂ when compared to the CdSe sensitized TiO₂ linked by short chain organic linker molecules.

3. Enhanced PEC Performance of CdSe QD-Sensitized Au/TiO₂ Hybrid Mesoporous Films

Metal NPs have also been considered for sensitizing of enhance PEC properties of metal oxides. We have demonstrated the first Au/TiO₂ hybrid structure (0-5%) that has also been sensitized with CdSe QDs for PEC water splitting. For the pristine TiO₂ film sample, the absorption onset is around 360 nm, with minimal visible light absorption. In contrast, the Au/TiO₂ film showed strong absorption in the visible region due to the surface plasmon resonance (SPR) of Au NPs, and the absorption increases with increasing amount of Au NPs loading. The strong enhancement for the photocurrent when Au is introduced with CdSe can be explained by an increase in scattering due to presence of the metal. The increase in scattering allows the CdSe to absorb more light and inject electrons into the conduction band of TiO₂. Since enhancement occurred over the entire visible spectral range and increased with decreasing wavelength, increased light scattering by Au NPs is suggested to be responsible for the enhanced PEC performance.

4. N-Doped ZnO Nanowire Arrays for PEC Water Splitting

N-doped zinc oxide (ZnO:N) nanowire arrays have also been studied as photoanodes in PEC hydrogen generation from water splitting. In comparison to ZnO nanowires without N-doping, ZnO:N nanowires show an order of magnitude increase in photocurrent density with photo-to-hydrogen conversion efficiency of 0.15% at an applied potential of +0.5 V (versus Ag/AgCl). These results suggest substantial potential of metal oxide nanowire arrays with controlled doping in PEC water splitting applications.

5. Photocatalytic Performance Improved in Nanorod Arrays

One way to effectively increase the photocatalytic performance of TiO₂ is to couple it with a metal, such as Ag, in order to create an effective charge-separation between the photogenerated electron-hole pairs. Ag NPs with different loadings were systematically coated onto uniformly aligned TiO₂ nanorod arrays, and their photocatalytic performance was found to be enhanced compared to bare TiO₂, and increased linearly with the Ag NP loading until a maximum photodegradation rate was reached at 0.25 wt.% Ag loading, and then decreased linearly with further increasing Ag loading. A simple reaction model was developed to explain the experimental results. Using two consecutive glancing angle depositions (GLAD) at different deposition angles and with different material, a WO₃-core TiO₂-shell nanostructure has been fabricated. The core-shell nanostructures are much more efficient in the amount of photodegradation abilities that can be extracted per nm of TiO₂ deposited. For the

core-shell nanostructures annealed at $T_a = 300^\circ\text{C}$, this ratio is 470 times, 90 times, and 18 times more efficient than the amorphous TiO₂, anatase TiO₂, and multi-layered TiO₂/WO₃ films. This huge improvement can be directly correlated to the larger interfacial area between TiO₂ and WO₃, which is optimized in this core-shell morphology.

Both WO₃/TiO₂ and TiO₂/WO₃ core/shell nanorod films were used to make electrodes for PEC water splitting. IPCE analysis showed that the WO₃/TiO₂ samples were more efficient at water splitting. The maximum efficiency for the TiO₂/WO₃ sample was under 5% at about 340 nm. The WO₃/TiO₂ achieved near 12% IPCE at 350 nm but the efficiency decreased sharply around 390 nm. These preliminary data show that the WO₃ is the better core material for these core/shell structures but improved efficiency in the visible region through sensitization or doping may allow these structures to achieve greater efficiency. Additional characterization will be needed to determine why the two structures showed such a marked difference in water splitting efficiency.

6. Double-Sided QD Co-Sensitized ZnO Nanowire Arrays for PEC Hydrogen Generation

An analogue of the typical tandem cell for PV devices has been produced by designing a photoanode which is coated on both sides with conductive substrate (FTO) and ZnO nanowires. To increase the visible light absorption, both sides have been coated in either CdS or CdSe. This unique structure integrates the motif of QD sensitization and tandem cell to provide a simple approach to enhance simultaneously the visible light absorption and carrier collection of nanostructured metal oxide photoelectrodes. The electrode with the highest photocurrent and efficiency was when the CdS/ZnO nanowire side was illuminated with light loading compared to the CdSe/ZnO on the opposite end. Controls were done on various double sided as well as single sided structures. Linear sweep measurements for the CdS/ZnO-ZnO/CdSe double sided nanowire electrodes showed enhanced photocurrent when compared to control structures. This is due to the elevation of the CdSe when the Fermi energies are aligned increasing electron and hole transport. Recombination of electrons and holes is also less in these devices which increases their overall performance.

Future Directions

Our plan for next year include optimization of composite structures in terms of ratio and morphology of constituent components, validation of the enhanced hole transport model proposed using ultrafast laser techniques using the new fs laser system acquired recently, and improvement of overall PEC performance by carefully considering, determining and controlling the key factors involved, including electrode, interfacial interaction, and optical absorption. A combination of microscopy, spectroscopy, dynamics, and electrochemistry techniques will be employed. Collaboration with appropriate groups will be

sought, including possible theoretical modeling in relation to the experimental work.

References

1. J. Hensel, G. Wang, Y. Li, and J.Z. Zhang, "Synergistic effect of CdSe quantum dot sensitization and nitrogen doping of TiO₂ nanostructures for photoelectrochemical hydrogen generation", *Nano Letters*, 10, 478-483, 2010.
2. L. Liu, G. Wang, Y. Li, Y. Li, and J. Z. Zhang, "Enhanced photoresponse of CdSe quantum dot sensitized TiO₂ nanoparticles by plasmonic gold nanoparticles", *Nano Research*, in press, 2010.
3. G. Wang, X. Yang, F. Qian, J.Z. Zhang and Y. Li, "Double-sided CdS and CdSe quantum dot co-sensitized ZnO nanowire arrays for photoelectrochemical hydrogen generation", *Nano Letters*, 10, 1088-1092, 2010.

Publication list (including patents) acknowledging the DOE grant or contract

1. K.L. Knappenberger, Jr., W. Xu, D.B. Wong, A.M. Schwartzberg, A. Wolcott, J.Z. Zhang, and S.R. Leone, "Excitation wavelength dependence of fluorescence intermittency in CdSe/TOPO nanorods", *ACS Nano*, 2, 10, 2143-2153, 2008.
2. A. Wolcott, W. A. Smith, T. R. Kuykendall, Y.P. Zhao, and J.Z. Zhang "Photoelectrochemical generation of hydrogen from water splitting based on dense and aligned TiO₂ nanorod arrays", *Small*, 5, 104-111, 2008.
3. G. Wang, D. Chen, H. Zhang, S. Nespurek, J.Z. Zhang and J. Li, "Tunable photocurrent spectrum and enhanced photocatalytic activity of well-oriented zinc oxide nanorod arrays", *J. Phys. Chem. C*, 112, 8850-8855, 2008.
4. J.Z. Zhang, C.D. Grant, "Optical and dynamic properties of semiconductor nanomaterials", *Ann. Rev. of Nano Research*, 2, 1, 2008 (invited review).
5. W. Smith and Y.-P. Zhao, "Enhanced photocatalytic activity by aligned WO₃/TiO₂ two-layer nanorod array," *J. Phys. Chem. C*, 112, 19635 -19641 (2008).
6. Y.-P. He, Z.-Y. Zhang, and Y.-P. Zhao, "Optical and photocatalytic properties of oblique angle deposited TiO₂ nanorod array," *J. Vac. Sci. Technol. B* 26, 1350 - 1358 (2008).
7. T. Lopez-Luke, A. Wolcott, L. Xu, S. Chen, Z. Wen, J. Li, Elder de La Rosa-Cruz, and J.Z. Zhang, "Nitrogen doped and CdSe quantum dot sensitized nanocrystalline TiO₂ films for solar energy conversion applications", *J. Phys. Chem. C*, 112, 1282-1292, 2008.
8. J. Li and J.Z. Zhang, "Optical properties and applications of hybrid semiconductor nanomaterials", *Coord. Chem. Rev.*, 253, 3015-3041, 2009 (invited review).
9. Y. Li and J.Z. Zhang, "Hydrogen generation from photoelectrochemical water splitting based on nanomaterials", *Lasers and Photonics Review*, in press, 2009 (invited review).
10. Z. Wen, Y. Li, J. Li, J.Z. Zhang, "Metal oxide nanostructures for lithium-ion batteries" in book on "Metal Oxide Nanostructures and Their Applications", Chapter 3, 1-33, 2009.
11. A. Wolcott and J.Z. Zhang, "Multidimensional nanostructures for water splitting: synthesis, properties and applications"; invited book chapter for "On Solar Hydrogen and Nanotechnology" edited by L. Vayssieres, Chapter 15, pp. 459-506, 2009.
12. X. Yang, A. Wolcott, G. Wang, A. Sobo, B. Fitzmorris, F. Qian, J.Z. Zhang, and Y. Li, "Nitrogen-doped ZnO nanowire arrays for photoelectrochemical water splitting", *Nano Letters*, 9, 2331-2336, 2009.
13. W. Smith, W. Ingram, and Y.-P. Zhao, "The scaling of the photocatalytic decay rate with the length of aligned TiO₂ nanorod arrays," *Chem. Phys. Lett.* **479**, 270-273, 2009.
14. W. Smith and Y.-P. Zhao, "Superior photocatalytic performance by vertically aligned core-shell TiO₂/WO₃ nanorod arrays," *Catalysis Communications* **10**, 1117-1121, 2009.
15. R. Sharma, J.P. Mondia, J. Schäfer, W. Smith, S.-H. Li, Y.-P. Zhao, Z.H. Lu, and L.J. Wang, "Measuring the optical properties of a trapped ZnO tetrapod," *Microelectronics Journal* **40**, 520-522, 2009.
16. J. Hensel and J.Z. Zhang, "Effect of ions on photoluminescence of semiconductor quantum dots", *Science of Advanced Materials*, 1, 4-12, 2009.
17. R.W. Meulenberg, J.R.I. Lee, A. Wolcott, J.Z. Zhang, L.J. Terminello, and T. van Buuren, "Determination of the exciton binding energy in CdSe quantum dots", *ACS Nano*, 3, 325-330, 2009.
18. G. Chornokur, S. Ostapenko, E. Oleynik, C. Phelan, N. Korsunskaya, T. Kryshchuk, J.Z. Zhang, A. Wolcott, T. Sellers, "Scanning photoluminescent spectroscopy of bioconjugated quantum dots", *Superlattices and Microstructures*, 45, 240-248, 2009.
19. A. Wolcott, J.Z. Zhang, W.A. Smith, and Y.P. Zhao, "Photoelectrochemical Study of Nanostructured ZnO Thin Films for Hydrogen Generation from Water Splitting", *Advanced Functional Materials*, 19, 1849-1856 2009.
20. L. Liu, G. Wang, Y. Li, Y. Li, and J.Z. Zhang, "Enhanced photoresponse of CdSe quantum dot sensitized TiO₂ nanoparticles by plasmonic gold nanoparticles", *Nano Research*, in press, 2010.
21. A. Wolcott, R.K. Fitzmorris, O. Muzaffery, and J.Z. Zhang, "CdSe quantum rod formation aided By in situ TOPO oxidation" *Chem. Mater.*, 22, 2814-2821, 2010.
22. G. Wang, X. Yang, F. Qian, J.Z. Zhang and Y. Li, "Double-sided CdS and CdSe quantum dot co-sensitized ZnO nanowire arrays for photoelectrochemical hydrogen generation", *Nano Letters*, 10, 1088-1092, 2010.
23. J. Hensel, G. Wang, Y. Li, and J.Z. Zhang, "Synergistic effect of CdSe quantum dot sensitization and nitrogen doping of TiO₂ nanostructures for photoelectrochemical hydrogen generation", *Nano Letters*, 10, 478-483, 2010.

- 24.** L. Liu, J. Hensel, R.C. Fitzmorris, Y. Li, and J.Z. Zhang, "Preparation and photoelectrochemical properties of CdSe/TiO₂ hybrid mesoporous structures", *J. Phys. Chem. Lett.*, 1, 155-160, 2010.
- 25.** X.J. Lv, J.H. Li, Jennifer Hensel, Jin Z. Zhang, "Enhanced visible light photoelectrochemical performances with nitrogen doped TiO₂ nanowire arrays", *Electrochemistry*, 15, 432-440, 2009.
- 26.** W. Smith, S. Mao, G. Lu, A. Catlett, J. Chen, and Y. Zhao, "The effect of Ag nanoparticle loading on the photocatalytic activity of TiO₂ nanorod arrays," *Chem. Phys. Lett.* **485**, 171-175, 2010.
- 27.** C. Tansakul, E. Lilie, E.D. Walter, F. Rivera III, A. Wolcott, J.Z. Zhang, G.L. Millhauser and R. Braslau, "Distance-dependent fluorescence quenching and binding of CdSe quantum dots by functionalized nitroxide radicals", *J. Phys. Chem. C*, 114, 7793-7805, 2010.
- 28.** J. Hensel, M. Canin, J.Z. Zhang, "QD co-sensitized and nitrogen doped TiO₂ nanocomposite for photoelectrochemical hydrogen generation", *SPIE Proc.*, 7770, 121-128, 2010.
- 29.** J. Hensel and J.Z. Zhang, "Photogenerated charge carriers in semiconductor nanomaterials for solar energy conversion" *Int. Journal of Nanoparticles*, (invited key review), in press, 2010.
- 30.** J.Z. Zhang, "Metal oxide nanomaterials for solar hydrogen generation from photoelectrochemical
- 31.** J.Z. Zhang, A. Wolcott, J. Hensel, T. Lopez-Luke, and Y. Li, "QD sensitized and N-doped TiO₂ solar cells", U.S. Provisional Patent Application disclosed on May 1st, 2008.