



# ***Low-cost Magnetocaloric Materials Discovery***

Phase II STTR Project ID PD172

PI: Dr. Robin Ihnfeldt<sup>1</sup>

Team: Prof. Emeritus Sungho Jin<sup>1</sup>, Prof. Renkun Chen<sup>2</sup>, Dr. Xia Xu<sup>1</sup>,  
Elizabeth Caldwell<sup>2</sup>, and Eunjeong Kim<sup>2</sup>

<sup>1</sup>General Engineering & Research, L.L.C.

<sup>2</sup>University of California, San Diego  
Materials Science Department

2018 DOE Annual Merit Review

June 14, 2018

# Overview

## Timeline

Phase I Project Start Date: 06/13/2016

Phase II Project Start Date: 07/31/2017

Phase II Project End Date: 07/30/2019

## Budget

Total Project Budget: \$1,150,000

- Phase I - \$150,000
- Phase II - \$1,000,000
- Total DOE Funds Spent\*: \$450,000
- As of 3/31/18 – late start due to delay in funds

## Barriers

H. High-Cost and Low Energy Efficiency of Hydrogen Liquefaction

*Ultimate Target: Energy Required < 6 kWh/kg of LH2 at 300,000kg/day facility.*

## Partners

**UCSD** – Project Partner

**US DOE** – Project sponsor and funding

**California Energy Commission** – additional business development funding

**San Diego Region Energy Innovation Network**- Incubator for CleanTech companies Interactions/collaborations

- Hydrogen Delivery Tech Team
- Other Industrial Partners

# Relevance

Objective:

Develop low cost energy efficient magnetic refrigeration technology for hydrogen liquefaction.

## Barrier

### H. High-Cost and Low Energy Efficiency of Hydrogen Liquefaction

- Energy required for hydrogen liquefaction at point of production too high.
- Hydrogen boil-off from cryogenic liquid storage tanks needs to be minimized.

## PNNL Task (PD131)

Developing magnetocaloric hydrogen liquefaction prototype to establish viability of concept.

## GE&R Task

Discover, develop, and commercialize low cost high performance MCE alloys to enable magnetic refrigeration to move from prototype to production.

DOE Current Targets	FY 2015 Status	FY 2020 Target	Ultimate Target
<b>Small Scale Liquefaction (30,000 kg H2/day)</b>			
Installed Capital Cost (\$)	70 million	70 million	-
Energy Required (kWh/kg of H2)	15	12	-
<b>Large Scale Liquefaction (300,000 kg H2/day)</b>			
Installed Capital Cost (\$)	560 million	560 million	142 million
Energy Required (kWh/kg of H2)	12	11	6

# Relevance

Magnetic refrigeration is a promising breakthrough technology to replace conventional compression based systems.

## PROS


- ◆ Solid state material – NO HFCs
- ◆ Lasts forever
- ◆ High Efficiency (H<sub>2</sub> liquefaction >50% energy reduction)\*

## CHALLENGES

- ◆ Rare-Earth - \$ to \$\$\$\$
- ◆ Not easy to make - Processing \$\$\$\$
- ◆ Limited commercially available materials
- ◆ Limited work demonstrating these systems
- ◆ MCE material only works at its curie temp, T<sub>c</sub>

## Magnetocaloric Effect (MCE)

The variation in temperature of a magnetic material when exposed to a change in magnetic field.



# Approach

Objective: Discover, develop, and commercialize low cost high performance MCE alloys to enable magnetic refrigeration to move from prototype to production.

## Phase I Milestones - Completed

1.1 Discover low cost high performance MCE materials for sub 50K

## Phase II Milestones – In progress

2.1 Discover novel MCE materials for >50K temperature applications

2.2 Testing in Magnetic Refrigeration Environment

a) Characterize  $\Delta T$ .

b) Evaluate heat capacity/thermal transport – *Build prototype*


2.3 Optimize material synthesis processing to achieve:

a) High performance – need  $\Delta T$  equivalent or better than Gd

b) Low cost – Target selling price of \$5,000/kg

c) High stability form - spheres or thin plates

2.4 Commercially Available MCE Products on [www.geandr.com](http://www.geandr.com) webstore.




New!  
Small scale, room temp. Will need additional funding to achieve low temp.

# Approach

## MCE material cost vs. Magnetic Field Cost

Lots of work on MCE Materials in last few decades

- No known commercial magnetic refrigerators yet for >4K applications.



### Traditional Approach to MCE Materials Research

- Maximize  $\Delta S$ 
  - GdSiGe
  - LaFeSi
- Avoid rare-earth materials due to cost/availability
  - MnFeAs
  - NiMnSn

$\Delta S$  not a good measure of performance for 1<sup>st</sup> order materials.

Performance is too low


### GE&R Approach to MCE Materials – stems from experience building magnetic refrigeration devices

- Materials with 2<sup>nd</sup> order only response
  - Maximize  $\Delta T$  – high cooling power
  - Mechanically stable
- Use low cost rare-earth (Ce, Nd, Gd)
  - Need high performance to keep cost of Magnetic field reasonable


# Accomplishments and Progress

## MCE Materials 9K to 300K

For 9~50K,  
-> **Nd/Ce based ternary**



For 50~325K,  
-> **Nd/Gd ternary or quaternary**





NEW PATENTS FILED

Low cost 2<sup>nd</sup> order MCE compositions discovered for entire temperature range 9K – 325K

# Accomplishments and Progress

## MCE Materials High Performance

Ternary Gd-A-B compound (as-cast)



Significant Improvement in Performance with composition optimization.

For further performance improvements - Long high temp anneals typically required

**Challenge: low melting temperature**

- Anneal may not work to improve performance
- New melt furnace installed onsite

GOAL: Synthesize alloys on-site and optimize melt step to avoid additional anneal.





# Accomplishments and Progress

## High Stability Form – Spheres and Thin Plates

### Rotating Disk Atomization




- Performed by Arcast Inc
  - Sub mm size spheres
  - Performance maintained (or better)
  - Reasonable cost – several kg for \$1k
  - Our material works well
  - Process optimization needed
- Thin Plates – need to develop



Materials Successfully formed into sub mm size spheres

# Accomplishments and Progress

## Cryogenic/Magnetic System



- The magnetic field can reach up to ~0.37 T.
- The cryogenic chamber can reach down to 20 K.
- The chamber can be moved in and out of magnetic field by mechanical rotation.




**Custom built system to characterize  $\Delta T$  of MCE materials.**

- Measure  $\Delta T$  - This is a better indicator of performance
  - not easy to measure

# Accomplishments and Progress

## Characterizing MCE materials in Refrigeration Environment

### $\Delta T$ of Gd




Calculated  $\Delta T$  (based on DS curve)  $\sim 1.9 \text{ K}$  @ 0.37 T

Measured  $\Delta T \sim 0.5 \text{ K}$

Measured  $\Delta T$  of Gd

# Accomplishments and Progress

## Characterizing MCE materials in Refrigeration Environment






Cold head

Thermocouple

La-Fe-Si plate

### La-Fe-Si Plate




- Cryogenic chamber temperature:  $T = 190$  K (temp of max  $\Delta T$ )
- Magnetic field:  $H = 0.37$  T
- La-Fe-Si plate temperature change:  $\Delta T = 0.3$  K

$\Delta T$  of LaFeSi is lower than Gd, even though  $\Delta S$  is nearly triple

# Accomplishments and Progress

## Small Room Temperature Magnetocaloric Cooler Prototype



In progress. Testing material performance, compatibility, etc.

# Reviewer Responses

This project was not reviewed last year.

# A Collaborative Project

Partner	Project Role
US DOE	Project sponsor and funding
University of California, San Diego (UCSD)	Project partner. Subcontractor. Assisting with materials development and optimization.
California Energy Commission (CEC)	Additional funding provided for business development through CALSeed Program. Participation in CleanTech Open business accelerator program.
San Diego Regional Energy Innovation Network (SDREIN)	Networking incubator for CleanTech companies in San Diego. GE&R officially accepted into program. They provide network / mentor resources.
Hydrogen Delivery Tech Team	Annual reporting provided to HDTT
Other Industry Partnerships	In Progress - Proprietary

# Remaining Challenges and Barriers

## Magnetic Refrigeration

For MCE Materials Commercialization:

- MCE Materials - need continued process development and optimization to hit performance targets ( $\Delta T \sim 1^\circ\text{C}$  in 1T field) to be viable in magnetic refrigeration systems.
- Commercialization – MCE materials market is small. Very few entities are actually working on systems.
  - Need more resources to work on system development – we added small prototype development to our Phase II milestones. Additional resources will be needed to develop commercial systems.

For Hydrogen Liquefaction:

- Both large scale magnetic refrigeration production plants and small scale magnetic refrigeration systems to prevent boil-off at point of use are needed.
- Only two known entities working on systems (Pacific Northwestern National Lab and Japanese National Institute of Material Science). Need industrial effort to move magnetic refrigeration technology forward.



# Proposed Future Work

## Remainder FY2018 and FY2019

Phase II Milestones	Description	Percent Complete
1	<p>Discover MCE for &gt;50K applications</p> <ul style="list-style-type: none"><li>- Low cost compositions with 2<sup>nd</sup> order response to cover 9-300K range have been discovered. We will investigate material doping to improve performance. Additional material set (such as known and public domain alloys of Gd, Dy, Er) may be investigated if needed.</li></ul>	80%
2	<p>Evaluate performance in magnetic refrigeration environment</p> <ul style="list-style-type: none"><li>- We have a custom built platform to evaluate <math>\Delta T</math> of materials.</li><li>- We are working on a small scale room temperature prototype. Additional funding/ resources will be needed to develop:<ul style="list-style-type: none"><li>- LH2 production facility using Magnetic Refrigeration</li><li>- Zero boil-off magnetic refrigeration system for 1000kg LH2 gas station storage</li></ul></li></ul>	50%
3	<p>Optimize processing to achieve high performance, low cost, and stability.</p> <ul style="list-style-type: none"><li>- New furnace installed for on-site alloy synthesis. We will develop melting/cooling conditions to achieve high performance and methods to form material into thin plates.</li></ul> <p>Phase II Goal: 1kg available for \$5000</p>	50%
4	<p>Commercially Available MCE Products on <a href="http://www.geandr.com">www.geandr.com</a> webstore.</p> <ul style="list-style-type: none"><li>- Webstore is built. Just need to add products.</li></ul>	50%

Any proposed future work is subject to change based on funding levels.

# Technology Transfer Activities

## Additional Funding Received

- CALSeed Grant from the California Energy Commission is supporting business development activities for our Magnetic Refrigeration technologies.

## Potential Future Funding

- Applied for ARPA-E funding to develop Zero boil-off LH2 storage system.
- Applied for NASA SBIR Phase I to develop Zero boil-off LH2 storage system.
- We will compete in the CALSeed Phase II pitch competition in Sept 2018 to raise additional funds for prototype development.
- Industrial Funding Sources – In progress.

## Patents

- PCT application (US2018/012836) filed for our ternary based compounds.
- New provisional application (US 62/634078) filed on our quaternary compounds.
- New provisional application (US 62/551148) filed to cover zero boil-off LH2 storage system.

# Summary Slide

- Novel 2<sup>nd</sup> order response MCE material set for entire temperature range 9 - 325K discovered with promising potential for high refrigeration performance.
- System to characterize  $\Delta T$  developed.
- In-house manufacturing capabilities in progress.
- Additional CEC funding obtained for magnetic refrigeration development.

# Technical Back-Up Slides