

Non-Pt Catalysts for PEFCs

*Xiaoping Wang, Deborah Myers, and Nancy Kariuki
Argonne National Laboratory*

May 16-19, 2006

This presentation does not contain any proprietary or confidential information
Project ID # FCP 29



THE UNIVERSITY OF
CHICAGO

A U.S. Department of Energy laboratory
managed by The University of Chicago



U.S. Department of Energy
Energy Efficiency and Renewable Energy

Bringing you a prosperous future where energy is clean, abundant, reliable, and affordable

Work sponsored by U.S. Department of Energy,
Hydrogen, Fuel Cells and Infrastructure Technologies Program



Overview

Timeline

- Project start date:
October FY'03
- Project end date: Open
- Percentage complete: n/a

Budget

- Total funding: \$750 K
- Funding for FY'05: \$150 K
- Funding for FY'06: \$300 K

Barriers

- Barriers addressed
 - B. Cost
 - C. Electrode performance

Partners

- Los Alamos National Laboratory
- Prof. John Regalbuto, University of Illinois at Chicago
- Collaborations with BES-funded groups on characterization
- Regularly providing updates and soliciting feedback from FreedomCAR Fuel Cell Technical Team

Objective

- Develop a non-platinum cathode electrocatalyst for polymer electrolyte fuel cells to meet DOE targets
 - Promotes the direct four-electron transfer with high electrocatalytic activity (comparable to that of Pt) (**0.44 A/mg_{Pt} or 720 μA/cm² @0.9V**)
 - *O₂ reduction reaction (ORR) in acidic media (e.g, in PEFC)*
 - *Two-electron transfer*
$$\text{O}_2 + 2\text{H}^+ + 2\text{e}^- = \text{H}_2\text{O}_2$$
 - *Four-electron transfer*
$$\text{O}_2 + 4\text{H}^+ + 4\text{e}^- = 2 \text{H}_2\text{O}$$
 - *Four-electron process is desirable due to its higher efficiency and non-corrosive product*
 - Chemically compatible with the acidic polymer electrolyte (**5000h @80°C, < 40% electrochemical area loss**)
 - Low cost (**\$8/KW, 0.3 mg PGM/cm²**)

Approach

■ Bi-metallic systems (e.g., base metal, noble metal)


- Surface segregation of minor noble metal component to form protective layer
- Base metal component chosen to modify d-band center of noble metal making it more “Pt-like”
- Choice of bi-metallic systems is based on the surface segregation energies and d-band center shift
(Source: A.V. Ruban, H.L. Skriver, J.K. Nørskov, Phys. Rev. B, 59 (1999)15990)
- Examples: Bi-metallics of iridium, rhodium, and palladium
- Alternative supports to modify electronic properties of small metal particles (e.g., titania)

■ Metal centers attached to electron-conducting polymer backbones

- Allows easy control of spacing between metal centers
- Electron conductor in close proximity to reaction site can promote high catalyst utilization

The d-band centers of candidate noble metals can be shifted to desired value by alloying with base metals




- There is a relationship between the d-band center of the metal and its ORR activity - Nørskov-Hammer theory and results of LBNL group
- Pt₃Co has high ORR activity and, thus, a desirable d-band center (LBNL)



Progress vs. FY '06 Milestones


- Synthesize and determine the ORR activity of two metal center-polymeric, two bimetallic, and one ACNT systems (06/06)
 - Two metal center-polymeric systems
 - *Synthesized and tested two metal center moieties*
 - *Identification of electron conducting polymers as backbone is underway*
 - Two bimetallic systems
 - *Competed one Ir-based bimetallic system for material synthesis (nine compositions) and testing, including materials characterization*
 - *Synthesized one Pd-based bimetallic system (five compositions); testing and characterization is underway*
 - *Finished three more Au-based bimetallic systems*
 - One Aligned Carbon Nanotube system
 - *Tested ORR activity*
- Determine the long-term stability of the electrocatalyst with the highest ORR activity (09/06)

Solid solutions of Ir-BM nanoparticles have been formed on Vulcan carbon





- XRD shows that a solid solution is formed at 400°C
- TEM shows catalysts to have 2- to 10-nm diameter particles



The Ir to base metal ratio affects the ORR activity



Acid treated Ir:BM catalyst showed improved ORR activity




- TEM image indicates that acid treatment did not change particle size
- EDX results shows molar ratio of Ir to BM stayed the same after acid treatment







ORR current decreased as the heat treatment temperature increased (Ir:BM)




38Ir:62BM, Room Temperature, 10 mV/s, 1600 rpm



Coarsening of Ir:BM particles occurred at higher heat treatment temperatures




Nanoparticles of Pd-base metal alloy have been formed on Vulcan carbon





- Bimodal size distribution:
 - 2-5 nm and 10-20 nm
 - 10-20 nm particles more evenly distributed

Base metal increased ORR activity of palladium



Base metals enhance the ORR activity of Ir and Pd, but further improvement is needed




Supported metallic system	Ir-based			Pd-based		DOE 2010 target 0.9 V
	Ir	Ir-BM	BM	Pd	Pd-BM'	
ORR mass activity at 0.8 V per mg metal	20 μ A	65 μ A	3 μ A	8.4 mA	36.6 mA	440 mA (110 mA)

New synthetic approach for desired structure/morphology of bimetallics --- Metal core-organic shell approach


- Nanocrystalline cores encapsulated in a monolayer of organic molecular or surfactant shell have several advantages
 - Size and surface properties of nanoparticles are controllable
 - Organic shell protects nanoparticles from agglomeration
 - *Stable and highly monodisperse nanoparticles*
 - Interparticle interactions of the shell molecules confers spatial controllability in the assembly of the particles on support materials
 - Deliberate tailoring of the surface of the metallic core with suitable shell structures enables the morphology of the bimetallic composition to be very well controlled
 - Large volumes of pre-engineered nanoparticles can be efficiently produced

A procedure has been devised for bimetallic system


Step 1: Seed preparation




Step 2: Seed growth




Step 3: Assemble on support and remove the shell for activation




**TEM shows nanoparticle size and monodispersity control---
better shaped and more uniform particles than traditional method**



Particle size ~ 2 nm




Particle size ~ 3 nm



50 nm

- TEM of Ir on BM reveals size growth associated with overdeposition of Ir on BM nanoparticles used as seeds
- EDX analysis confirmed bimetallic composition consistent with synthetic feed amounts of metal precursors

ORR activity of cobalt metal centers attached to polymer backbones begins at 0.6 V



Summary

- Both supported Ir- and Pd-based bimetallic systems showed an ORR activity better than supported Ir and Pd alone
 - *ORR started at potential of 0.85 V and 0.93 V, respectively for Ir- and Pd- based system*
- XRD and TEM analysis indicates alloy formation and nanosize particles for both systems
- ORR activity was strongly influenced by type and composition of bimetallic system and catalyst preparation and processing conditions (e.g., acid treatment and heat treatment temperature)
- New synthetic approach is being explored to obtain desired structure/morphology

Future work

- Perform elevated temperature RRDE experiment to determine O₂ reduction mechanism (2e⁻ or 4e⁻ transfer) for Ir-based system
- For Pd-based system
 - ORR activity testing and TEM work for other compositions prepared
- Prepare and test the ORR activity of additional bimetallic systems identified
- Surface and bulk characterization to verify the desired catalyst composition/structure, particle size, and electronic properties by using various techniques such as XRD, TEM, SEM, FTIR of adsorbed CO, and TPD of CO
- Explore different synthesis methods and temperature treatments
- Perform electrochemical and chemical stability studies
- Fabricate and test a membrane-electrode assembly using newly-developed electrocatalysts

Acknowledgments

- J. Vaughey and T. Cruse for XRD
- J. Mawdsley for TEM
- M. Ferrandon for TPR and TPD
- J. Yang and D.J. Liu for preparing ACNT system

Publications

- “Polymer Electrolyte Fuel Cell Cathode Electrocatalysts”, Xiaoping Wang, Romesh Kumar, and Deborah J. Myers, Poster and Abstract, 2005 Fuel Cell Seminar, Palm Springs, CA, November 14-18, 2005

Response to FY '05 Reviewers' Comments

- “The work on bimetallic(Au-based), transition metal carbides and nitrides, and metal centers attached to electron-conducting polymer backbone is too broad area for such relatively small project”
 - *We have focused our effort on bimetallic systems*
- “Need to pull in other characterization techniques to better understand behavior of bimetallic system (microscopy, etc.).”
 - *We are characterizing catalysts by TEM, XRD, EDX, CO Temperature Programmed Desorption*
- “See no evidence that the claimed LANL collaboration is underway”
 - *Once material shows adequate activity in screening tests, LANL will fabricate MEAs*
- “The reason for the choice of the new catalysts was not evident”
- “Screening large number of non-Pt catalysts based on Au is no guarantee that one of the proposed catalyst formulations will work”
 - *We have elaborated on the rationale behind the choice of bimetallic systems in this presentation*